

**General Description**

Nippon Paint 2<sup>nd</sup> Generation Super 5-in-1 Interior Emulsion Paint is a high performance interior emulsion paint. It provides a fungus resistant, scrub resistant, covers hairline cracks and washable finish that retains its attractive appearance for interior.

**Features**

- Good washability
- Water resistance
- Fungus and alkali resistance
- Covers hairline cracks

**Recommended For**

- Interior masonry surfaces
  - Hospitals
  - Schools
  - Restaurants
  - Shops
  - Offices
  - Public places
  - Residential buildings
  - Commercial buildings

**General Information**

Colour:	White, standard colours as per colour card and Nippon Paint 1881 colour creations	Drying time: (at 25 °C)	Surface dry: 1 hrs Hard dry: 2 hrs
Type:	Styrene-acrylic emulsion	Overcoat Time: (at 25 °C)	2~3 hrs
Finishes:	Matt	Full Curing (at 25 °C)	7 days
Application Method:	Brush / Roller / Airless spray	Specific Gravity: (at 25 °C)	1.3 (White)
Theoretical Coverage:	13~15 m <sup>2</sup> /L/coat	Solid Content: (by volume)	50%
Dilution:	Brush and Roller - ~20% clean water Airless Spray - ≤ 10% clean water	Packing:	1L / 5L / 18L
Dry Film Thickness:	30µm	Shelf Life:	24 months in sealed original packaging stored at room temperature and shaded place.

# Nippon Paint 2<sup>nd</sup> Generation Super 5-in-1 Interior Emulsion Paint

## Technical Data

<u>Test</u>	<u>Test Method</u>	<u>Result</u>
VOC Content (g/L)	USEPA Method 24	<50

### Recommended Painting System

Sealer/Primer: One coat of Vinilex 5101 Wall Sealer or Odourless-less Color Sealer  
Top Coat: Two coats of 2<sup>nd</sup> Generation Super 5-in-1 Interior Emulsion Paint

### Surface Preparation

All surface must be clean, dry and free from oil, grease, dirt, contaminants and loose materials.

- Dirt/Powder: Clean with damp cloth. Mild detergent may be used.
- Paint: Remove unstable or old film by high-pressure wash, or scraper whichever is appropriate.
- Plaster: Remove by chisel or power grinder. Replaster to unstable surface with an approved mortar mixture.
- Moisture: High moisture causes paint defect. The moisture content of substrate should be less than 6% or 19 determined by Protimeter. All water seepage must be checked and rectified.
- pH Value: pH value should be less than 10.
- Fungus: Remove by high-pressure wash & treat with Nippon Paint Anti-Fungus Solution
- Oil/Grease: Clean off with mild detergent and a little solvent. Wash thoroughly to remove all trace.

❖ **Ensure fresh air ingress while applying and before dry done**

❖ **High humidity and cool temperature will result in longer drying time**

### Limitations

Avoid painting when the temperature is below 5°C or the humidity is over 85%. Do not paint when raining and rain is expected during painting or drying process.

### Clean Up

Wash painting tools with water immediately after use.

### Safety Information

Keep out of reach of children. If medical advice is needed, get the product container or label at hand for easy reference.

Be aware of sanding dust / spray mist. Protective gloves, eye or face protection are highly recommended. Keep away from sparks, heat, open flames and any other ignition sources.

Eating, drinking and smoking should be prohibited in areas where the material is handled, stored and processed.

In case of eye contact, rinse immediately with plenty of water. For splashed skin, clean thoroughly with soap and water. Seek medical attention if indication persists.

If you experience difficulties on breathing, leave applied area and obtain fresh air. If difficulties continue, immediately get medical attention.

Product must always be stored in a ventilated, cool and dry place.

Tightly close product container after each use.

### Flash Point and Ignition Point

Flash Point: N/A  
Ignition Point: N/A

Note: The information given applies to the product and its performance under specific test condition. Due to the varied circumstances beyond our control under which the product may be applied, for specific applications, please contact Nippon Paint Project Sales Department. We reserve the right to modify our product specification without prior notice.

For further enquiries, please call:

**Nippon Paint (H.K.) Co., LTD**

Tel: (852) 2699 9333

Fax: (852) 2602 8844

Website: <http://www.nipponpaint.com.hk>