

NIPPON TEXTURED COATING SERIES



■ Repaint



Colors



All colours are subject to the original paint colour.

NIPPON TEXTURED COATING SERIES

Gloss Level (Color: NP-75B18) Low Gloss(15-20%) Semi-Gloss(35-45%) Gloss (Over 60%) Popular Colors NP-10PB19 NP-05R20 NP-05R11 NP-05YR34 NP-10R18 NP-05P18 NP-05R27 NP-10RP10 NP-05YR33 NP-05YR41 NP-05P02 NP-05R09 NP-05R25 NP-10YR33 NP-25YR26 NP-05P09 NP-05RP01 NP-05YR09 NP-05YR10 NP-10YR11 NP-75B01 NP-05GY01 NP-10YR10 NP-10YR02 NP-10YR13 NP-75B03 NP-75GY02 NP-75YR27 NP-05Y05 NP-05YR13 NP-75B13 NP-05GY26 NP-05GY29 NP-05Y07 NP-10RP16

All colours are subject to the original paint colour.

NP-NN12

NP-10YR15

NP-05BG22

NP-125Y03

NP-10R31

NIPPON TEXTURED COATING SERIES



All colours are subject to the original paint colour.

NIPPON TEXTURED COATING SERIES

Description

Texture products are widely used in both interior and exterior area. We provide water-based Acrylic, Polyurethane, Silicone & Fluorocarbon top coat which can be applied on the top of texture, suitable apply in both new and repainting projects.

Standard Painting Specification

Appliable Substrates

- · Concrete & plastered surfaces
- · Panels & fiber board
- · Ceiling board
- · Timber panel
- · Cement rendering
- · Partition
- · Mosaic tile

Standard Painting Systems

Substrate \ Coats	Tile Filler	Sealer	Texture	Mid-coat	Top Coat	
New Surface w/o Texture						
New Surface with Texture		0	0	0	0	
Mosaic Tiles	0	0	0	0	0	
Repaint w/o texture		0		0	0	
Repaint with texture		0	0	0	0	

Points for Application

Suggested Treatment

ouggoot	odggoddd ffodiffoli		
Dirt/Powder	_	High-pressure wash (External). Clean with damp cloth (Internal). Mild detergent may be used. For powdery surface, a coat of sealer is recommended.	
Paint	_	Remove unstable film by high-pressure water wash, or scraper which ever is appropriate.	
Plaster	_	Remove by chisel, power grinder etc. Re-plaster to a stable surface with an approved mortar mixture.	
Moisture	_	High moisture causes paint defect. Make sure the surface is dry prior to subsequent paint mixture. All seepages must be checked and rectified.	
Fungus	_	Remove by high-pressure water wash & treat with NIPPON ANTI-FUNGUS SOLUTION. Rinse again with clean water and dry.	
Oil/Grease		Clean off with mild detergent and a little solvent. Wash thoroughly to remove all trace.	

my inspiration, my Nippon Paint



NIPPON PAINT (H.K.) CO., LTD

Tel : (852) 2699 9333 Fax : (852) 2602 8844

Email: np@nipponpaint.com.hk

www.nipponpaint.com.hk