

**General Description**

Nippon Paint Yawa Silicone is a water-based elastic paint formulated with silicone resin. It has water resistance, dirt resistance, alkali resistance, weathering resistance, fungus resistance and anti-carbonation properties, providing excellent performances and all-round protections for exteriors.

**Features**

- Elastic
- Dirt resistance
- Alkali resistance
- Anti-carbonation property
- Fungus resistance
- Weathering resistance
- Water resistance

**Recommended For**

- Exterior masonry surfaces
  - Hotels
  - Schools
  - Residential buildings
  - Commercial buildings
  - Industrial buildings

**General Information**

Colour:	Standard colours	Drying time: (at 20°C)	Touch dry: 1 hr Dust free: 2 hr
Type	Water-based modified silicone resin	Overcoat Time: (at 20°C)	≥ 6 hrs
Finishes:	Matt	Full Curing (at 25 °C)	7 days
Application Method:	Porous roller / Wool roller	Specific Gravity: (at 20 °C)	1.32 ± 0.03
Theoretical Coverage:	0.14~0.18 kg/m <sup>2</sup> /coat	Solid Content: (by volume)	52%
Dilution:	5~10% clean water	Packing:	20 kg
Dry Film Thickness:	30 μm	Shelf Life:	36 months in sealed original packaging stored at room temperature and shaded place.

## Technical Data

<u>Test</u>	<u>Test Method</u>	<u>Result</u>
VOC Content (g/L)	USEPA Method 24	<50
Anti-Carbonation Test (R, m)	EN 1062-6	329
Water Vapour Diffusion Resistance (Sd (m))	EN ISO 7783	4
Water Permeability	ASTM E514	No Leakage
Sound Reduction (dB)	BS EN ISO 140-3 : 1995	6 dB
Resistance to Mild Acids	ASTM D1308	No discernible change
Resistance to Mild Alkali	ASTM D1308	No discernible change
Fungus Resistance	Ref .ASTM G21-15	No growth (The rating is 0)

### Recommended Painting System

Sealer/Primer: One coat of Ultra Sealer III  
Top Coat: Two coats of Yawa Silicone

### Surface Preparation

All surface must be clean, dry and free from oil, grease, dirt, contaminants and loose materials.

Dirt/Powder: High-pressure wash.

Paint: Remove unstable or old film by high-pressure wash, or scraper whichever is appropriate.

Plaster: Remove by chisel or power grinder. Replaster to unstable surface with an approved mortar mixture.

Moisture: High moisture causes paint defect. The moisture content of substrate should be less than 6% or 19 determined by Protimeter. All water seepage must be checked and rectified.

pH Value: pH value should be less than 10.

Fungus: Remove by high-pressure wash & treat with Nippon Paint Anti-Fungus Solution

Oil/Grease: Clean off with mild detergent and a little solvent. Wash thoroughly to remove all trace.

❖ **Ensure fresh air ingress while applying and before dry done**

❖ **High humidity and cool temperature will result in longer drying time**

### Limitations

Avoid painting when the temperature is below 5 °C or the humidity is over 85%. Do not paint when raining and rain is expected during painting or drying process.

### Clean Up

Wash painting tools with water immediately after use.

### Safety Information

Keep out of reach of children. If medical advice is needed, get the product container or label at hand for easy reference.

Be aware of sanding dust / spray mist. Protective gloves, eye or face protection are highly recommended. Keep away from sparks, heat, open flames and any other ignition sources.

Eating, drinking and smoking should be prohibited in areas where the material is handled, stored and processed.

In case of eye contact, rinse immediately with plenty of water. For splashed skin, clean thoroughly with soap and water. Seek medical attention if indication persists.

If you experience difficulties on breathing, leave applied area and obtain fresh air. If difficulties continue, immediately get medical attention.

Product must always be stored in a ventilated, cool and dry place.

Tightly close product container after each use.

### Flash Point and Ignition Point

Flash Point: N/A

Ignition Point: N/A

Note: The information given applies to the product and its performance under specific test condition. Due to the varied circumstances beyond our control under which the product may be applied, for specific applications, please contact Nippon Paint Project Sales Department. We reserve the right to modify our product specification without prior notice.

For further enquiries, please call:

**Nippon Paint (H.K.) Co., LTD**

Tel: (852) 2699 9333

Fax: (852) 2602 8844

Website: <http://www.nipponpaint.com.hk>

**General Description**

Nippon Paint Ultra Sealer III is a high performance water-based alkali-resistant acrylic sealer which is formulated to prevent deterioration of top coat by strong concentration of cement chemicals and provides a better surface condition for top coat to adhere on. With elastic property, water resistance, fungus and algae resistance, it gives a good performance and protection for interior and exterior surfaces.

**Recommended For**

- Interiors and exteriors
  - Cement plaster
  - Concrete
  - Quality skim coat

**Features**

- Elastic
- Excellent adhesion
- Quick drying
- Excellent alkali resistance
- Water resistance
- Fungus and algae resistance
- Efflorescence resistance

**General Information**

Colour:	Clear / White	Drying time: (at 30°C)	Touch dry: 10 mins
Type:	Modified acrylic copolymer	Overcoat Time: (at 25°C)	2 hrs
Finishes:	Matt	Full Curing (at 25 °C)	7 days
Application Method:	Brush / Roller /Airless spray	Specific Gravity: (at 25 °C)	1.04 ~1.11
Theoretical Coverage:	12m <sup>2</sup> /L/coat	Solid Content: (by volume)	36.5
Dilution:	Brush/Roller - max 30% water (Internal) - max 20% water (External) Spray - max 20% water (Internal) - max 10% water (External)	Packing:	18L
Dry Film Thickness:	30µm	Shelf Life:	36 months in sealed original packaging stored at room temperature and shaded place.

# Ultra Sealer III

## Technical Data

<u>Test</u>	<u>Test Method</u>	<u>Result</u>
VOC Content (g/L)	USEPA Method 24	<100
Formaldehyde (mg/kg)	GB 18582-2008	21
Heavy Metal - Lead (mg/kg)	GB 18582-2008	ND
Heavy Metal - Cadmium (mg/kg)	GB 18582-2008	ND
Heavy Metal - Chromium (mg/kg)	GB 18582-2008	ND
Heavy Metal - Mercury (mg/kg)	GB 18582-2008	ND
Condition in Container	JIS K5400 : 1990 4.1	There was no lumps, no separation and no coagulation of the ingredients
Hardness (Pencil Scratch Value)	JIS K5400 : 1990 8.4.2	H
Film Appearance	JIS K5400 : 1990 7.1	Appearance of film is normal
Water Resistance	JIS K5400 : 1990 8.19	Unchanged when immersed 96 hours in tap water
Alkaliproof	JIS K5400 : 1990 8.21	Unchanged when immersed 48 hours in saturated solution of calcium hydroxide
Water Permeability (ml)	JIS A 6909-1995	0.23
Adhesion Strength (Under Normal Condition, N/cm <sup>2</sup> )	JIS A6910 : 1988 5.8	200
Adhesion Strength (Immersion in Water, N/cm <sup>2</sup> )	JIS A6910 : 1988 5.8	211.66
Permeability (ml)	JIS A 6910 : 1998 5.10	0

\*ND = Not Detected

# Ultra Sealer III

---

## Surface Preparation

All surface must be clean, dry and free from oil, grease, dirt, contaminants and loose materials.

- Dirt/Powder: High-pressure wash (External). Clean with damp cloth (Internal). Mild detergent may be used.
- Paint: Remove unstable or old film by high-pressure wash, or scraper whichever is appropriate.
- Plaster: Remove by chisel or power grinder. Replaster to unstable surface with an approved mortar mixture.
- Moisture: High moisture causes paint defect. The moisture content of substrate should be less than 6% or 19 determined by Protimeter. All water seepage must be checked and rectified.
- pH Value: pH value should be less than 10.
- Fungus: Remove by high-pressure wash & treat with Nippon Paint Anti-Fungus Solution
- Oil/Grease: Clean off with mild detergent and a little solvent. Wash thoroughly to remove all trace.

❖ **Ensure fresh air ingress while applying and before dry done**

❖ **High humidity and cool temperature will result in longer drying time**

## Limitations

Avoid painting when the temperature is below 5°C or the humidity is over 85%. Do not paint when raining and rain is expected during painting or drying process

## Clean Up

Wash painting tools with water immediately after use.

## Safety Information

Keep out of reach of children. If medical advice is needed, get the product container or label at hand for easy reference.

Be aware of sanding dust / spray mist. Protective gloves, eye or face protection are highly recommended. Keep away from sparks, heat, open flames and any other ignition sources.

Eating, drinking and smoking should be prohibited in areas where the material is handled, stored and processed.

In case of eye contact, rinse immediately with plenty of water. For splashed skin, clean thoroughly with soap and water. Seek medical attention if indication persists.

If you experience difficulties on breathing, leave applied area and obtain fresh air. If difficulties continue, immediately get medical attention.

Product must always be stored in a ventilated, cool and dry place.

Tightly close product container after each use.

## Flash Point and Ignition Point

Flash Point: N/A

Ignition Point: N/A

Note: The information given applies to the product and its performance under specific test condition. Due to the varied circumstances beyond our control under which the product may be applied, for specific applications, please contact Nippon Paint Project Sales Department. We reserve the right to modify our product specification without prior notice.

For further enquiries, please call:

**Nippon Paint (H.K.) Co., LTD**

Tel: (852) 2699 9333

Fax: (852) 2602 8844

Website: <http://www.nipponpaint.com.hk>